



Landscapus INC
Products Manual

HR (High Retroreflectivity) Glass Beads

Direct-Melt Virgin Glass Made

Item	Standard
Appearance	Outer clean and transparent, without visible bubble and impurity.
Density	2.4-2.6 g/cm ³
Bulk Density	1.57g/cm ³
Roundness	>90%
Refractive Index	1.5 Min.
Composition	SiO ₂ content: 71-74%
Softening Degree	720-730 centigrade
Retroreflectivity	>700mcd/lux/m ²

AASHTO M247-13 Type 3

>1700	0
1400-1700	0-5
1180-1400	0-10
1000-1180	40-85
850-1000	5-40
<850	0-5

AASHTO M247-13 Type 4


>2000	0
1700-2000	0-5
1400-1700	0-20
1180-1400	40-85
1000-1180	5-40
<1000	0-5

AASHTO M247-13 Type 5

>2350	0
2000-2350	0-5
1700-2000	0-10
1400-1700	40-85
1180-1400	5-40
<1180	0-5

TT-B-1325D Type IV

Micron	Type 4 A	Type 4 B
1700	100	100
1400	95-100	
1180	80-95	95-100
1000	10-40	
850	0-5	35-70
600		0-5



AS /NZS 2009: 2006 Glass beads: Type BHR, Type CHR, Type DHR

Landscapus Inc, Your Reliable Partner



Landscapus Inc **Your Reliable Partner**

Know More From Our Website



Add : 1-909, Xuanlifang, Shunyi,

Beijing, P.R. China

Tel : +86 10 61428699

Fax : +86 10 69450772

Email : marketing@landscapus.com

Web : www.landscapus.com